

CHROME SAND METALLURGICAL GRADE

ANALYSIS		TYPICAL %	
Cr ₂ O ₃		44%	Minimum Guaranteed
SiO ₂		4.5%	Maximum Guaranteed
FeO		26.5%	
Al ₂ O ₂		15.5%	
CaO		0.3%	
MgO		10.5%	
TiO ₂		0.7%	
V ₂ O ₅		0.45%	
P		0.005%	
S		0.005%	
Cr:Fe Ratio		1.48:1	
SIZING			
-1 mm		98%	
PACKING			
Loose Bulk Wet			

Information above is given in good faith as accurate but not guaranteed to be a specification. No guarantee is given or implied. Users should conduct tests to determine suitability for any specific purpose.